

8 Bis, Rue Gutenberg
Z.I. La Marinière
91070 Bondoufle France

Phone. : 01.69.11.50.50
Fax : 01.69.11.50.51

Mail : contact@brasage.com
Web site : www.brasage.com

NORMES	EN ISO 1044/1999.....	B - Cu80PAg-645/800
	Abrégé	CP 102
	DIN 8513	L-Ag 15 P
	Norme BS 1845.....	CP 1
	Custom Code	74082100

CADMIUM FREE

COMPOSITION (value %)	Ag : 14 - 16	Cu : 79 - 81	P : 4 - 6
----------------------------------	--------------	--------------	-----------

TECHNICAL DATA	Rm Kg /mm ² à 20°c	65
	A % à 20°c	10
	Range of fusion	650 - 800 °C
	Density	8.4

COLOURS AND PACKAGING	Fluxcoated	No available
	Dimension	Lenght 500 mm, diameter 15/10, 20/10 et 30/10

QUALITY		norme DIN 8513 with each case .
	(on request)	norme Din 8513 and batch number on each rod.
	(on request)	Analysys certificat.

SECURITY DATA SHEET Download www.brasage.com..

DESODIXIZING	PASTE	: Carboflux blanc et Carboflux NT
	POWDER	: Superflux – Superflux MX – Maxiflux

LIABILITY DISCLAIMER Alliages Industries sarl, seeks to represent reliable information concerning the composition, properties and use of its products. The technical information provided in this publication is provided at no charge and is without guarantee, warranty or responsibility of any kind, expressed or implied.